

PAROPY CL 147

APPLICATION INSTRUCTIONS

STEP BY STEP

Step 1

Feed material into laser printer so that the printer is printing on the printable side (white matte coated side).

Step 2

Design your image and and resize if necessary

Step 3

Prepress fabric for 5-10 seconds

Step 4

Place on shirt with image face down.

Step 5

Heat apply the transfer onto the fabric. Press at 385-400F at 25-30 seconds. Use Maximum pressure

Step 6

Peel backing off hot.

APPLICATION

Paper Mode	Heavy to Label*
Image	Mirror
Press Time:	25 sec.
Temperature:	375F (190C)
Pressure:	Maximum
Peel:	Hot
Wash Temp.:	Up to 105F (40C)

*These settings are recommended, you may need to conduct your own tests
All technical information and recommendations are based on tests we have conducted.
Users should conduct their own tests before proceeding

NOTES

Recommended Fabrics

White or Light Colored
100% cotton
100% polyester
Poly/cotton blends
Polyester knits
Polyester mesh
Poly/foam & cotton caps
Satin
Fabric Puzzles

Accessories Required

Computer, Color Laser Copier/Printer,
Heat Press.

Printable side

The printable side (white matte coated side) without the red lettering.

Pressure Settings

To ensure that the coating has properly fused with the fabric, we recommend to use maximum pressure. If this paper is applied with inadequate pressure, the transfer will not wash well.

Care Instructions

Wait 24 hours before washing.
Machine wash using mild detergent.
Do not use bleach or other aggressive cleaning agents. Cannot be dry cleaned. Wash Temperature cannot exceed 105F

Storage

CL 147 has an indefinite shelf life when stored at room temperature. Keep away from direct heat, sunlight and humidity.